

ALLOY/ALLIAGE	Alloy composition d'alliage (%)										
	Cu	Sb	Cd	Bi	As	Pb	Ni	Fe	Zn	Al	Sn
<b>ASTM #2 (ASTM B 23-94)</b>	3,0-4,0	7,0-8,0	0-0,05	0-0,08	0,10 max	0-0,35	N/A	0,08 max	0,005 max	0,005 max	Balance
<b>Thermodyne</b>	9,4-10,0	9,35-9,85	N/A	N/A	N/A	Low	0,25-0,50	N/A	N/A	N/A	Balance
<b>Royal Nickel Geniune</b>	3,0-,40	7,0-8,0	0-0,05	0-0,08	0,10 max	0-0,35	0,30-0,50	0,08 max	0,005 max	0,005 max	Balance